



PAPERS

you can trust

FOOD CONTACT

TECHNICAL SPECIFICATION

These products have Isega Certificates in accordance with the characteristics of each.

The **Food Contact** products can be used in direct contact with food. If greasy or moist foods are used, and if no specific barrier is applied, the packaging may present food marks. The product is completely recyclable and compostable.

Albus	CIE Whiteness 144	By order from 160 to 315 g/m ²	It may stand in direct contact with dry and fatty foodstuffs. See ISEGA Certificate of compliance.
Prado Natura	Without Optical Brightener	By order from 160 to 315 g/m ²	It may stand in direct contact with dry, moist and fatty foodstuffs. See ISEGA Certificate of compliance.
CLK	Produced with unbleached kraft pulp	By order from 180 to 280 g/m ²	It may stand in direct contact with dry, moist, and some kinds of fatty foodstuffs. See ISEGA Certificate of compliance.

ALBUS


Property	Reference Standard	Units	Nominal Value				
Basis Weight	ISO 536	g/m ²	160	180	210	240	315
Taber Stiffness	MD	mN.m	1.8	2.3	4.0	5.0	8.0
	CD		0.9	1.2	2.0	2.5	4.0
Thickness	ISO 534	µm	190	210	240	280	350
Bekk Smoothness	ISO 5627	s	27	23	23	23	23
Moisture Content	ISO 287	%	7.5	7.5	7.5	7.5	7.5
CIE Whiteness	ISO 11475	%	144.0	144.0	144.0	144.0	144.0

MD-Machine Direction; CD-Cross-Machine Direction

Product certifications available



EU Ecolabel: PT/011/003



www.papeldoprado.com

This information is subject to change without notice.
Last update: 07/2024



PAPERS

you can trust

FOOD CONTACT

TECHNICAL SPECIFICATION

PRADO NATURA

Property		Reference Standard	Units	Nominal Value
Basis Weight		ISO 536	g/m ²	180
Taber Stiffness	MD	ISO 2493	mN.m	2.8
	CD			1.4
Thickness		ISO 534	μm	225
Bekk Smoothness		ISO 5627	s	23
Moisture Content		ISO 287	%	6.5

MD-Machine Direction; CD-Cross-Machine Direction

CLK

Property		Reference Standard	Units	Nominal Value		
Basis Weight		ISO 536	g/m ²	180	240	280
Taber Stiffness	MD	ISO 2493	mN.m	3.0	7.0	12.0
	CD			1.5	3.0	4.5
Thickness		ISO 534	μm	230	310	370
Burst Index		ISO 2758	KPa.m ² /g	3.5	2.5	2.5
Moisture content		ISO 287	%	7.5	7.5	7.5

Cross-Machine Direction

MD-Machine Direction; CD-

Product certifications available



EU Ecolabel: PT/011/003



www.papeldoprado.com

This information is subject to change without notice.
Last update: 07/2024