

ESPECIFICACIONES TÉCNICAS

Propiedad		Referencia Estándar	Unidad	Valor Nominal							
Gramaje		ISO 536	g/m ²	135	150	170	190	225	250	300	350
Rigidez Taber	DL	ISO 2493	mN.m	1.0	1.8	2.0	3.0	4.5	5.0	7.0	11.5
	DT			0.5	0.9	1.0	1.5	2.2	2.5	3.2	5.5
Espesor		ISO 534	μm	155	175	200	220	260	290	335	385
Lisura Bekk		ISO 5627	s	35	27	23	23	23	23	23	23
Humedad		ISO 287	%	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5
Blancura CIE		ISO 11475	%	163	163	163	163	163	163	163	163

DL-Dirección Longitudinal (Sentido de Fibra); DT-Dirección Transversal (Contra Fibra)


ESPECIFICACIONES DEL PRODUCTO

Gramaje (g/m ²)	Dimensiones (cm)	Paquete por palet	Resmas por palet	Hojas por paquete
135	65x92	28	14	250
	70x102	28	14	
150	65x92	24	12	250
	70x102	24	12	
170	65x92	40	10	125
	70x102	40	10	
190	65x92	36	9	125
	70x102	36	9	
225	65x92	32	8	125
	70x102	32	8	
250	65x92	28	7	125
	70x102	28	7	
300	65x92	30	6	100
	70x102	30	6	
350	65x92	25	5	100
	70x102	25	5	

Certificaciones del producto disponibles



EU Ecolabel: PT/011/003



www.papeldoprado.com